



مصنع رأس الخيمة

للمواد اللاصقة والعازلة ركام ش.ذ.م.م

RAS AL KHAIMAH

ADHESIVE & WATERPROOF MATERIALS FACTORY RAKAM LLC



TECHNICAL CATALOGUE



FLOORING
& TILING



WATER
PROOFING



BONDING
AGENTS



SEALANTS
& REPAIR
MORTARS



SPECIALITY
PRODUCTS



TECHNICAL DATA SHEET



RAKAM



105 RAK NS GROUT

(Non-Shrink Grout)

RAK NS GROUT is a pre-mixed, cementitious non-shrink grout which requires only the addition of water to obtain a free flowing non-shrink grout of excellent performance.

ADVANTAGES	RESISTANCE TO HIGH TEMPERATURE:	ORDERING GUIDE													
<ul style="list-style-type: none"> • Non-shrink • Pre-mixed and packed to avoid site variations and errors • High bond strength to steel and concrete • High early strength characteristics for rapid return • Adjustable consistency • High strength, impact resistance and durability • Non-shrink properties give maximum contact with bearing surfaces • Can be used up to a 80 mm thickness between plate and foundation 	<p>RAK NS Grout can withstand high temperature (+400°C) for very long periods without deteriorating substantially.</p>	<p>PRODUCT NO. 105</p> <p>STANDARDS ASTM C - 191, 878, 230 ASTM C - 827-78</p> <p>PACKAGING 25kg Paper / Plastic Bags</p> <p>COLOR Grey</p>													
	RESISTANCE TO CHEMICAL ATTACK	STORAGE													
	<p>RAK NS Grout is watertight and is protected against environmental aggressive agents in solution.</p>	<p>RAK NS Grout should be stored in dry premises, away from direct sunlight, wind and humidity</p>													
APPLICATION	COMPRESSION STRENGTH														
<p>Mix the powder with measured quantity of water for a minimum of 5 minutes to obtain a smooth, uniform lump free consistency. Approximately 5-6 liters of water is needed for 25 kg of powder. Pour the grout continuously to eliminate air pockets. For a thick consistency, 4-5 litres of water should be used and for dry packs 2.5 - 3 liters of water should be used.</p>	<p>N/MM2AT 20°C (BS/1881 Pt 116-1983)</p> <table border="1"> <tr><td>Day</td><td></td></tr> <tr><td>1</td><td>28</td></tr> <tr><td>7</td><td>57</td></tr> <tr><td>28</td><td>65</td></tr> </table>	Day		1	28	7	57	28	65						
Day															
1	28														
7	57														
28	65														
<p>USES</p> <ul style="list-style-type: none"> • Repair to pre-cast concrete • Bedding bearing plates and grouting • Floor repairs and toppings • Heavy machinery and equipment foundations • Pre-fabricated unit joints and cable grouting 	FLEXURAL STRENGTH														
	<p>N/MM2AT 25°C (BS-4551 1980)</p> <table border="1"> <tr><td>Day</td><td></td></tr> <tr><td>1</td><td>5.2</td></tr> <tr><td>7</td><td>8.7</td></tr> <tr><td>28</td><td>10.8</td></tr> </table>	Day		1	5.2	7	8.7	28	10.8						
Day															
1	5.2														
7	8.7														
28	10.8														
TYPICAL PROPERTIES		HEALTH AND SAFETY													
<table border="0"> <tr><td>Appearance</td><td>Powder</td></tr> <tr><td>Apparent Density</td><td>1.4gm/cc</td></tr> <tr><td>Grain Size</td><td>0.4mm 1.2mm</td></tr> <tr><td>Adhesion on - Concrete</td><td>26.8 Bar</td></tr> <tr><td>Color</td><td>Grey</td></tr> <tr><td>Expansion Perios</td><td>120 Minutes</td></tr> <tr><td>Expansion - Chrcacterstics</td><td>Max 2.2% @ 24 Hours</td></tr> </table>		Appearance	Powder	Apparent Density	1.4gm/cc	Grain Size	0.4mm 1.2mm	Adhesion on - Concrete	26.8 Bar	Color	Grey	Expansion Perios	120 Minutes	Expansion - Chrcacterstics	Max 2.2% @ 24 Hours
Appearance	Powder														
Apparent Density	1.4gm/cc														
Grain Size	0.4mm 1.2mm														
Adhesion on - Concrete	26.8 Bar														
Color	Grey														
Expansion Perios	120 Minutes														
Expansion - Chrcacterstics	Max 2.2% @ 24 Hours														
BOND TO STEEL	SUPPORT														
<p>The bond of RAK NS Grout to steel, calculated by applying loads to the bars undergoing pull-out tests and by the grout steel contact surface is:</p> <p>For plain bars: 3 N/mm² at 7 days 4 N/mm² at 28 days</p> <p>For deformed bars: 20 N/mm² at 7 days 30 N/mm² at 28 days</p>	<p>Supports should be sound, clean and free of dust, demoulding materials, oil, paint, etc. Clean the area to be grouted with water 24 hours prior to grouting. The surface should be damp but strictly free of standing water. The bolt holes and other areas should be water free. Bare plates, bolts, etc. must be clean and free of oil, grease paint, etc. The form works should be leak proof.</p>														
	CLEANING														
	<p>Tools should be cleaned with water</p>														



RAKAM



P.O. BOX 11005, RAS AL KHAIMAH - U.A.E

+9717 266 8383 +9717 266 8853

sales@rakam.ae www.rakam.ae



HIGH
QUALITY



FAST
DELIVERY



BEST
PRICES

مصنع رأس الخيمة

للمواد اللاصقة والعازلة ركام ش.ذ.م.م

RAS AL KHAIMAH
ADHESIVE & WATERPROOF MATERIALS FACTORY RAKAM LLC

Customer Care
+971 55 4040456

FLOORING & TILING

WATER PROOFING

BONDING AGENTS

SEALANTS & MORTARS

SPECIALITY PRODUCTS