



مصنع رأس الخيمة

للمواد اللاصقة والعازلة ركام ش.ذ.م

RAS AL KHAIMAH

ADHESIVE & WATERPROOF MATERIALS FACTORY RAKAM LLC



TECHNICAL CATALOGUE



FLOORING
& TILING



WATER
PROOFING



BONDING
AGENTS



SEALANTS
& REPAIR
MORTARS



SPECIALITY
PRODUCTS





RAKAM


TECHNICAL DATA SHEET

203 RAK TILE FIX-WP

Water Resistant Tile Adhesive



RAK TILE FIX WP is a ready mix polymer modified cement based tile adhesive. It is composed of grey or white colour powder and does not contain fiber, asbestos or any other harmful components.

ADVANTAGES	INSTRUCTIONS FOR USE																																							
<ul style="list-style-type: none"> • High bond strength • Water resistant • Economical • Eco-friendly • Tropical grade • Formulated to suit Middle East conditions 	<p>Surface Preparation</p> <p>All surfaces should be sound, clean & uncontaminated. This preparation should leave an exposed concrete surface free from dust, loose particles, deleterious matter, oil, grease, chemical films & other contaminant.</p> <p>All loose particles of mortar, paint, etc. must be physically removed.</p> <p>Concrete or blockwork: allowed to cure sufficiently so that all shrinkage movements take place before fixing tiles.</p> <p>Gypsum supports: treat with 304-5. Should not have a percentage of humidity more than 10%.</p> <p>The surface of substrates must be moistened slightly with clean water to reduce the absorption of water from the mortar. Do not moistened the tiles.</p>	<p>Place the tiles onto the adhesive bed. Apply sufficient pressure on the tile during fixing it with slight twisting movement in order to ensure good contact with the adhesive.</p> <p>In case of large size tiles, it is necessary to spread the adhesive also to the backside of the tile and then place the tiles into the adhesive bed.</p> <p>Apply enough material that can be tiled during the adhesive's open wet time. Spreading large areas may result in drying the adhesive before tiles can be fixed causing poor adhesion.</p>																																						
<p>USES</p> <p>RAK TILE FIX WP is used for permanent fixing of ceramic tiles for internal applications.</p> <p>It may be suitable for use in :</p> <ul style="list-style-type: none"> • Kitchens • Bathrooms • Regular Rooms 																																								
<p>TECHNICAL PROPERTIES</p> <table border="1"> <thead> <tr> <th>Properties</th> <th>Result</th> </tr> </thead> <tbody> <tr><td>Appearance</td><td>Powder</td></tr> <tr><td>Color</td><td>Grey or White</td></tr> <tr><td>Dry Density</td><td>1.55 kg/L</td></tr> <tr><td>Wet Density</td><td>1.70 kg/L</td></tr> <tr><td>VOC</td><td>3.4 g/L</td></tr> <tr><td>Water resistance</td><td>Excellent</td></tr> <tr><td>Open Time</td><td>Approx. 20 minutes</td></tr> <tr><td>Workable Time</td><td>45 minutes</td></tr> <tr><td>Wall Grouting</td><td>After 10 hours</td></tr> <tr><td>Floor Grouting</td><td>After 24 hours</td></tr> <tr><td>Ready to Use</td><td>After 14 days</td></tr> <tr><td>Shear Strength (ANSI 118.1)</td><td>>0.85 N/mm²</td></tr> <tr><td>Adhesion Strength (EN 1348)</td><td></td></tr> <tr><td>Initial adhesion at 28 days</td><td>1.22 N/mm²</td></tr> <tr><td>Adhesion after heat</td><td>0.57 N/mm²</td></tr> <tr><td>Adhesion after water immersion</td><td>0.59 N/mm²</td></tr> <tr><td>Adhesion after Freeze-the cycle</td><td>1.00 N/mm²</td></tr> <tr><td colspan="2">All values are subject to 5-10 % tolerance</td></tr> </tbody> </table>	Properties	Result	Appearance	Powder	Color	Grey or White	Dry Density	1.55 kg/L	Wet Density	1.70 kg/L	VOC	3.4 g/L	Water resistance	Excellent	Open Time	Approx. 20 minutes	Workable Time	45 minutes	Wall Grouting	After 10 hours	Floor Grouting	After 24 hours	Ready to Use	After 14 days	Shear Strength (ANSI 118.1)	>0.85 N/mm ²	Adhesion Strength (EN 1348)		Initial adhesion at 28 days	1.22 N/mm ²	Adhesion after heat	0.57 N/mm ²	Adhesion after water immersion	0.59 N/mm ²	Adhesion after Freeze-the cycle	1.00 N/mm ²	All values are subject to 5-10 % tolerance		<p>MIXING</p> <p>Place 5.0 – 5.25 liters of cold, potable water (or Bond SBR as needed) in the mixing bucket and add slowly 25 kg bag of RAK TILE FIX WP under continuous mixing till a uniform lump free consistency mix is achieved. For mixing process, a slow speed drill (200- 300rpm) fitted with a suitable paddle is recommended.</p> <p>Allow the obtained mix to stand for about 5 minutes and then remix before application.</p>	<p>FINISHING</p> <p>Remove excess adhesive with a damp cloth before it dries. Joints grouting between tiles may be commenced after 10 hours of tiling for walls and 24 hours for floors.</p>
Properties	Result																																							
Appearance	Powder																																							
Color	Grey or White																																							
Dry Density	1.55 kg/L																																							
Wet Density	1.70 kg/L																																							
VOC	3.4 g/L																																							
Water resistance	Excellent																																							
Open Time	Approx. 20 minutes																																							
Workable Time	45 minutes																																							
Wall Grouting	After 10 hours																																							
Floor Grouting	After 24 hours																																							
Ready to Use	After 14 days																																							
Shear Strength (ANSI 118.1)	>0.85 N/mm ²																																							
Adhesion Strength (EN 1348)																																								
Initial adhesion at 28 days	1.22 N/mm ²																																							
Adhesion after heat	0.57 N/mm ²																																							
Adhesion after water immersion	0.59 N/mm ²																																							
Adhesion after Freeze-the cycle	1.00 N/mm ²																																							
All values are subject to 5-10 % tolerance																																								
	<p>APPLICATION</p> <p>Spread RAK TILE FIX WP on the substrate to a uniform thickness using a toothed spatula, the first pass with its straight edge and the second pass immediately after, to the desired thickness of RAK TILE FIX WP using the toothed part.</p>	<p>CLEANING</p> <p>Tools and equipment should be cleaned with water immediately after use. Hardened materials should be mechanically removed.</p>																																						
		<p>RECOMMENDATIONS</p> <ul style="list-style-type: none"> • To achieve improve adhesion strength, it is recommended to replace water with Bond SBR. • The grey type presents higher mechanical resistances. It is therefore advisable to use to fix tiles on floor 																																						

<ul style="list-style-type: none"> Stiffened mortar must neither be diluted with water nor with fresh mortar Do not use RAK TILE FIX WP on metal or non-absorbing surfaces. Do not apply RAK TILE FIX WP in rainy weather, high winds and sand storms Do not apply under direct sun Keep equipment cool and use cold water Porosity of tiles and substrates has significant effect on adhesive strength of tile 	<p>CONSUMPTION</p> <p>Approx. 4 to 4.5 kg RAK TILE FIX WP per m² using notched trowel on smooth surface. Consumption will vary according to type of tiles and support condition.</p>	<p>HEALTH & SAFETY</p> <p>RAK TILE FIX WP can be harmful to skin as it contains cement powders which may release alkalis when mixed with water.</p> <p>During application, wear appropriate protective clothing, goggles, gloves and respiratory equipment if necessary.</p> <p>In case of contact with skin, rinse with water and again wash thoroughly with soap and water. In case of contact with eyes, rinse with plenty of water and seek medical advice accordingly.</p> <p>If ingested, obtain medical attention immediately. Do not induce vomiting.</p>
	<p>STORAGE</p> <p>Store in dry covered place in the original closed bags and shelf life is 12 months if stored as recommended.</p>	
	<p>ORDERING GUIDE</p> <p>PRODUCT NO. 203</p> <p>STANDARDS BS-5980 Type 1 Class A BS-5385 Part 1</p> <p>PACKAGING 20 kg / 25 kg Paper / Plastic Bags</p> <p>COLOR White / Grey</p>	
	<p>APPLICABLE STANDARDS</p> <ul style="list-style-type: none"> EN 12004 ISO 13007 ANSI A 118.1 EN 1346 EN 1348 ANSI A 118.4 (SBR) 	





RAKAM



P.O. BOX 11005, RAS AL KHAIMAH - U.A.E

+9717 266 8383 +9717 266 8853

sales@rakam.ae www.rakam.ae



HIGH
QUALITY



FAST
DELIVERY



BEST
PRICES

مصنع رأس الخيمة

للمواد اللاصقة والعازلة ركام ش.ذ.م.م

RAS AL KHAIMAH
ADHESIVE & WATERPROOF MATERIALS FACTORY RAKAM LLC

Customer Care
+971 55 4040456

FLOORING & TILING

WATER PROOFING

BONDING AGENTS

SEALANTS & MORTARS

SPECIALITY PRODUCTS