

TECHNICAL DATA SHEET

STELLAR

ستيلار



RAKAM





المعلومات الفنية

TECHNICAL DATA SHEET

STALLER PRIMER SEALER

DESCRIPTION & FIELD OF APPLICATION

A quick drying, general-purpose water based primer sealer/undercoat, designed for use as primary coat for emulsion paint systems, to penetrate and seal the surface for better adhesion and preventing absorption of highly porous surfaces. It is suitable for interior application on concrete, plaster, cement and gypsum.

MAIN FEATURES

- Excellent adhesive strength.
 - High penetrating power.
 - Flow and leveling properties.
 - Good hiding power.
- * A second coat can be applied after two hours...*

PHYSICAL SPECIFICATION

- Specific gravity
- Solid by volume
- Coverage rate
- Dry film thickness
- Shelf life
- Flash point
- Finish
- Drying time at 25 °C
- Approx. 1.39 g/cc
- Approx. 29%
- 9-11 M²/Liter
- 25 Microns
- 12 months
- Not applicable
- Matt
- "Surface dry approx. 1 hour
Hard dry approx. 2 hours"

SURFACE PREPARATION

The surface should be sound, dry and clean, free from dirt, oil, grease, and loose paint, or powdery materials...

A- OLD PAINTED SURFACES

- 1- Remove the old paint as much as possible.
- 2- Sand the entire surface and remove all the dust.
- 3- Wash down with Ammonia Water Solution.
- 4- Rinse with clean water and allow to dry.
- 5- Prime the surface to be painted with STELLAR Primer Sealer or STELLAR Latex Sealer.
- 6- Fill cracks and holes with STELLAR Wall Putty or STELLAR Acrylic Filler.
- 7- After drying, sand the putty and clean the surface once again.
- 8- Apply two coats of STELLAR Interior Emulsion."

B- NEW SURFACES

- 1- Sand the surface until completely smooth, remove all the dust.
- 2- Prime the surface to be painted with STELLAR Primer Sealer or STELLAR Latex Sealer.
- 3- Apply 1-2 Coats of STELLAR Wall Putty or STELLAR Acrylic Filler.
- 4- After drying, sand the putty and clean the surface.
- 5- Apply two coats of STELLAR Interior Emulsion.

INSTRUCTION FOR USE

Airless Spray Gun

- Type of thinner Clean Water
- Percentage of thinning 10 – 15% max. by volume
- Nozzle orifice 0.015" – 0.018"
- Output pressure 120 – 140 bar

Air spray gun

- Type of thinner Clean Water
- Percentage of thinning 10 – 15% max. by volume
- Nozzle orifice 1.5 – 2.0 mm
- Output pressure 2 – 3 bar

Brush / Roller

- Type of thinner Clean Water
- Percentage of thinning 10 – 20% max. by volume

SUBSEQUENT COATS

STELLAR Gloss Emulsion
 STELLAR Exterior Acrylic Emulsion
 STELLAR Polyurethane Gloss Enamel 2K

PACKING

18 Lt./drum , 4lt gallon

COLOURS

White

REMARKS

- Stir well before use...
- Avoid application below 5 °C or over 85% relative humidity.
- After painting, clean the application tools immediately with water.
- Close container after use.
- Store in a cool and dry place.
- Keep out of reach of children.
- For more information, please do not hesitate to contact our Technical Department.

STELLAR

ستيلار



RAKAM

مصنع رأس الخيمة للمواد اللاصقة والعازلة راكم ش.ذ.م.ح.
ص.ب. : 11005 رأس الخيمة إ.ع.م.، تليفون : 8383 266 971+ فاكس : 8853 266 971+
بريد إلكتروني : sales@rakam.ae موقع إلكتروني : www.rakam.ae

RAS AL KHAIMAH ADHESIVE & WATERPROOF MATERIALS FACTORY RAKAM LLC
P.O. Box 11005, Ras Al Khaimah - U.A.E, Tel +9717 266 8383, Fax +9717 266 8853,
E-mail: sales@rakam.ae, Web: www.rakam.ae