



المعلومات الفنية  
TECHNICAL DATA SHEET

RAKAM QUICK DRYING ENAMEL

PRODUCT CODE: RAKAM - 710

DESCRIPTION

Rakam Industrial Quick Drying Enamel is a one component, quick drying, solvent based, glossy alkyd enamel. It is formulated with a modified alkyd that provides quick drying and an attractive and durable finish.

TECHNICAL DATA

- Solid by volume : 50 ± 2% (ASTM D 2697 )
- Theoretical spreading : 12.5 m<sup>2</sup>/L
- Dry film thickness : 40 microns
- Wet film thickness : 80 microns
- Flash point : 25°C (ASTM D 3278)
- Finish : Glossy –Shades available in RAKAM
- VOC : <410 g/L (ASTM D 3960)

APPLICATION DATA

**Surface preparation:** Coated surface:

All surfaces should be clean, dry and free from contamination. Surfaces should be treated in accordance with ISO 8504:2000. Ensure compatibility of the coated substrates with the selected paint system. If the remaining part of the existing coating system needs to be sweep-blasted, fine abrasive shall be used to avoid damage to the coating system. When recoating aged coated substrates, damaged areas must be removed back to a firm edge. Light abrade or sweep-blast the surface in order to provide a physical key for adhesion

**Minor repair/Touch up:**

All surfaces should be clean, dry and free from contamination. Surfaces should be treated in accordance with ISO 8504:2000. Any corroded areas should be prepared by power-tool cleaning or

manual cleaning.

Power-tool cleaning to min. St 2, preferably St 3 (ISO 8501- 1:2007). Care shall be taken to ensure that power- tool cleaning does not polish the steel surface. If the surface being prepared lies adjacent to a coated surface, the power tool cleaning shall overlap the coated surface by at least 25 mm and the coated surface shall be feathered.

**Typical coating system**

Primer : Rakam Quick Dry Primer : 40μ

Topcoat: Rakam Quick Dry Enamel: 40μ

**Application method :** Brush/ Roller

Applicable for inaccessible area, corners and edges. Multiple coat may be required for desired film thickness.

- Volume of thinner : 5-10%
- Mixing ratio : Single pack
- Airless spray : Pressure at nozzle : 2000 - 2200 psi  
Nozzle size: 0.011 - 0.015 inch  
Spray angle: 40 - 80°  
Volume of thinner: 5 - 10%
- Air assisted gun : Pressure at nozzle : 35 - 50 psi  
Nozzle size : 1.8 - 2.2mm  
Spray angle: 40 - 80°  
Volume of thinner: 10 - 15%

**Conditions:**

- Humidity : Below 85% RH
- Temperature of the substrate should be at least 3°C above the dew point of the air.
- Application temperature : Mini: 10°C, Maxi: 45°C
- Thinner/Cleaner : Rakam QD Thinner
- Pot life : Not applicable
- Packaging : Available in 3.6 Liters & 18 Liters



CURING TIME

- Touch Dry : 2 hours @ 10°C  
: 1 hours @ 20°C  
: 20 minutes @ 30°C  
: 10 minutes @ 40°C
- Dry to handle : 24 hours @ 10°C  
: 16 hours @ 20°C  
: 8 hours @ 30°C  
: 6 hours @ 40°C
- Recoat interval Min : 24 hours @ 10°C  
Max : Indefinite\* @ 10°C  
Min : 16 hours @ 20°C  
Max : Indefinite\* @ 20°C  
Min : 8 hours @ 30°C  
Max : Indefinite\* @ 30°C  
Min : 6 hours @ 40°C  
Max : Indefinite\* @ 40°C

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product and should be considered as guidelines only. The actual drying time/times may be shorter or longer, depending on film thickness, temperature, ventilation, humidity, preceding paint system etc.

\*The surface should be dry and free from contaminants prior to over coating. The best intercoat adhesion is achieved when the subsequent coat is applied before the preceding coat is fully cured. When recoating with products, maximum recoat interval is limited. After prolonged exposure it may be necessary to roughen the surface to ensure intercoat adhesion. When in doubt, consult RAKAM LLC representative.

HEALTH & SAFETY

Avoid skin and eye contact by wearing overalls, gloves, goggles, and mask etc.

Eyes: In the event of accidental splash, flush eye with water immediately and obtain medical advice.

Skin: Wash skin thoroughly with soap and water or medically approved cleaner.

Avoid inhalation of vapors and paint mist by wearing suitable mask. In the event of ingestion seek medical attention immediately.

This product is flammable, keep away from sources of ignition. Take precautionary measures against static discharge. In the case of fire –blanket flames with foam, carbon dioxide or dry chemicals.

Painting must be carried out in well-ventilated area. Local safety regulation need to be followed.

HANDLING AND STORAGE

Product must be stored according to local regulations and manufacturer recommendation. Recommended to store at 30°C, away from direct sunlight, heat, source of ignition and exposure to water or rain, within a well ventilated place.

Shelf life@ 24 months in original sealed drums from the date of manufacture when stored at or below 30°C

ADVANTAGES & RECOMMENDED USES

It is suitable topcoat that can be applied over various single pack or two pack primers. It requires no mixing and has no pot life restriction, giving low application cost with minimum wastage. Possess good adhesion & flexibility which makes it suitable topcoat to be applied over surfaces such as wood metals and masonry.